

TOP tapes[®]

Copper Tape

TTO COT50

Material: C11000 Alloy

C11000

Typical Properties	VALUE	UNIT
Thickness	0.050 ± 0.005	mm
Elongation at Break	>15.4	%
Tensile Strength	>292.3	N/mm ²
Hardness	>98.6	HV
Purity of CU	>99.9	%
20°C Resistivity (Conductivity)	≥98.5%	Ω.mm ² /m (%IACS)
Cu	>99.96	%
Fe	≤0.002	%

The figures shown above are typical value and should not be used as the basis of specification.