

TOP tapes®

Copper Tape

TTO COT75

Material: C11000 Alloy

C11000

Typical Properties	VALUE	UNIT
Thickness	0.075 ± 0.005	mm
Elongation at Break	> 20	%
Tensile Strength	> 200	Mpa
Hardness	> 50	HV
Purity of CU	> 99.9	%
Resistivity (Conductivity)	≤ 0.018699 ($\geq 99\%$)	$\Omega \cdot \text{mm}^2 / \text{m}$ (%IACS)
Cu	> 99.97	%
Fe	≤ 0.004	%

The figures shown above are typical value and should not be used as the basis of specification.