

TOP tapes[®]

non-conductive waterblocking nonwoven tape

TTO 212

Composition :

- PES nonwoven fabric
- Polyacrylate swelling powder

PROPERTY	TEST METHOD	VALUE	UNIT
Weight	ISO 9073/1	120± 10	g/m ²
Thickness	ISO 9073/2	0.30 ± 0.05	mm
Tensile strength	ISO 9073/3	≥ 35	N/cm
Elongation	ISO 9073/3	>10	%
Swelling speed	TTO method	>7	mm/1.min
Swelling height	TTO method	>12	mm/3.min
Short term stability	TTO method	230	°C
Long term stability	IEC 216	90	°C
Moisture content 23±2	TTO method	< 10	%

The figures shown above are typical value and should not be used as the basis of specification.